

Dynax[®] heavy body



Technical Data Sheet

Intended use: Dental impression material on the basis of vinylpolysiloxane

Indication: Addition vulcanising, thixotropic, pressure-forming precision pre-impression material especially for the sandwich, correction and double mixing technology.

Manufacturer: Dreve Dentamid GmbH
Max-Planck-Straße 31
59423 Unna / Germany

Composition:

Pos	Chemical term
1	Polyvinylmethylsiloxane
2	Polydimethylsiloxane Oil
3	Silicic acid
4	Filling materials
5	Polymethylhydrogensiloxane
6	Platinum catalyst
7	Pigments
8	Additives

Properties:

Colour: sky blue

Hardness: 70 ± 3 Shore A (DIN ISO 7619-1)

Consistency: heavy-bodied - type 1 (DIN EN ISO 4823)

Recovery from deformation: > 99.8 % (DIN EN ISO 4823)

Linear dimensional change: < 0.2 % (DIN EN ISO 4823)

Tensile strength: ≥ 4,0 MPa (DIN 53504)

Tear resistance: ≥ 3,0 N/mm (ISO 34-1)

Processing time: 90 sec at 23 °C

Deflasking time: 90 sec at 37 °C

Dreve Dentamid GmbH
Max-Planck-Str. 31
59423 Unna / Germany
Tel.: 02303 / 8807-40
Fax: 02303 / 8807-55
dentamid@dreve.de
www.dreve.com