

# Laborsil pro 70



## Technisches Datenblatt

**Intended use:** Addition-vulcanising kneadable silicone for the universal use in the dental lab with a final hardness of 70 Shore A

**Manufacturer:** Drewe Dentamid GmbH  
Max-Planck-Straße 31  
59423 Unna / Germany

### Composition:

Pos	Chemical term
1	Polyvinylmethylsiloxane
2	Silicic acid
3	Fillers
4	Polymethylhydrogensiloxane
5	Platin-catalyst
6	Pigments

### Properties:

Colour: light grey

Hardness Shore A:  $70 \pm 3$

Processing time: 1:15 min. at 23°C

Setting time: > 6 min. at 23°C

Consistency: Type 0: kneadable

Recovery from deformation: > 99.2% (ISO 4823)

Deformation under pressure: 3% (ISO 4823)

Linear dimensionel change: < 0.2% (ISO 4823)

Drewe Dentamid GmbH  
Max-Planck-Str. 31  
59423 Unna / Germany  
Tel.: 02303 / 8807-0  
Fax: 02303 / 8807-55  
dentamid@drewe.de  
www.dentamid.drewe.de